



SL srl - via dell'Artigianato 13/15, 20882 Bellusco (MB) Italy  
ph. +39 039 6011239 • fax+39 039 2124935 • P.IVA 06386430968  
e-mail: info@s-line.it • www.s-line.it



## COARSE

January 2019

### Description:

Black high thickness anti-slip tape composed by PVC carrier coated with corundum mineral granules 24 grit, and modified acrylic solvent adhesive. The thickness of the grit, make it suitable for extreme applications where a normal anti-slip tape cannot work because of accumulation of dirt, mud, debris, etc. Particularly recommended to make sure surfaces like scaffolds, tractors, tanks, tankers etc. Suitable to outdoor applications, excellent resistance to trampling, weathering, UV rays, oils, detergents and solvents. Available in rolls and die-cut strip form. Apply to clean and dry surface.

### TECHNICAL DATA SHEET

|   |                                     |
|---|-------------------------------------|
| <b>Adhesive:</b>                        | Modified solvent acrylic            |
| <b>Carrier:</b>                         | Corundum coarse-grit (24 grit)      |
| <b>Liner:</b>                           | White single sided PE coated paper  |
| <b>Applied weight:</b>                  | 1.2 g/m <sup>2</sup>                |
| <b>Elongation:</b>                      | 5 %                                 |
| <b>Roll ball test (PSTC6):</b>          | 1 cm                                |
| <b>Peel adhesion (PSTC1):</b>           | 13 +/- 2 N/25mm                     |
| <b>Static coefficient of friction:</b>  | Dry leather 1.01<br>Wet rubber 1.30 |
| <b>Dynamic coefficient of friction:</b> | Dry leather 0.74<br>Wet rubber 1.02 |
| <b>Holding power:</b>                   | ≥ 48 hours                          |
| <b>Tensile strength:</b>                | ≥ 140 N/25mm                        |
| <b>Impermeability:</b>                  | 12 months                           |
| <b>Temperature resistance:</b>          | - 30° + 110°C                       |
| <b>Application temperature:</b>         | Between 18°C and 35°C               |
| <b>Shelf life:</b>                      | 12 months                           |

### Ageing in following liquid immersion:

|   |               |
|---|---------------|
| Water or detergents:  | over 72 hours |
| Petrol or fuel:   | over 72 hours |
| Diesel oil:   | 6 hours       |
| Brake liquid:   | 10 hours      |
| Engine oil:   | 30 hours      |
| Bum test: 5,5" char at 1300°C for 4 minutes, will not sustain after flame is cut off. |               |

The above performance features are based on the results of tests and careful calculations. They are put forward in good faith but are not guaranteed. The enduser should check the suitability of the product for its intended use and consult us for any doubt about particular applications. Storage should be in dry, well ventilated rooms with a temperature around 20°C and protected from continuous exposure to direct sunlight. Always apply the product to clean and dry surfaces.