



Test Report

Photographic Activity Test according to ISO 18916:2007-06

Summary: The material described below has **passed** the criteria for enclosure materials defined in ISO 18916:2007 "Photographic activity test for enclosure materials".

PTS Test-Report: **35776**

Material description: **130 my D/S Transfer tape**

Supplied by: **SL SRL**

on **03.03.2023**

Via dell'Artigianato 13/15, 20882 Bellusco MB

Test Results

1. Image Interaction Test

The material shall not produce a percentage image interaction effect in the colloidal silver fade detectors greater than a relative difference of more than $\pm 20\%$ compared to the control.

Density change of control: **-1,42**

Density change of material: **-1,55**

Relative difference: **9%**

2. Stain Test

The material shall not produce a mean stain in the photographic paper stain detector that is greater than the mean stain produced by the filter paper controls plus 0.08 density units.

Density change of control: **0,10**

Density change of material: **0,16**

Difference: **0,06**

3. Mottle Test

The enclosure material shall not produce *easily recognizable* mottling.

Visual assessment: **Passed**


Testing period: **20.03.-11.04.2023**

Sample-ID: **024-12**


Date Test Report **11.04.2023**

Papiertechnische Stiftung (PTS)

Pirnaer Straße 37, D-01809 Heidenau, Germany


Dr.-Ing. Birgit Lutsch

Lab. Manager Materials Testing


Nicole Brandt

PAT Project Manager

Papiertechnische Stiftung is
accredited according to
ISO/IEC 17025.

